

The Impact of Hydrophilic Coatings on Medical Device Performance: A Comprehensive Review

Kothwala Dr. Deveshkumar¹, Lad Hiren², Lad Nirav^{*3}

^{1,2,3} Meril Medical Innovations Private Limited, Bilakhia House, Survey No. 879, Muktanand Marg, Chala, Vapi, Dist-Valsad, Gujarat, 396191, India.

ABSTRACT

Hydrophilic coatings—specialized surface treatments composed of water-attracting polymers that form lubricious, hydrated layers when exposed to bodily fluids—have revolutionized the field of medical device surface modifications by significantly enhancing device performance through friction reduction, improved biocompatibility, and minimized adverse biological responses. These coatings consist primarily of hydrophilic polymers that, upon hydration, create smooth interfaces that facilitate easier navigation through tissues, minimize trauma during minimally invasive procedures, and reduce complications such as thrombosis and infections. This comprehensive review examines the chemical composition of hydrophilic coatings, their physicochemical mechanisms, and clinical applications. We discuss performance benefits, manufacturing challenges, and regulatory considerations, followed by insights into emerging innovations like stimuli-responsive coatings, antimicrobial integration, and biomimetic nanostructures. By highlighting current knowledge gaps and future directions, this article aims to provide an authoritative resource on hydrophilic coatings in modern medical device design and patient care.

KEYWORDS: Hydrophilic coatings, Antimicrobial coatings, Surface modification, Biocompatibility, Friction reduction, Anti-fouling properties, Polyvinylpyrrolidone (PVP), Polyethylene glycol (PEG), Minimally invasive procedures, Biomimetic nanostructures, Device-related infections, Regulatory considerations

ARTICLE DETAILS

Published On:
29 November 2025

Available on:
<https://ijmscrs.com>

1. INTRODUCTION

1.1 The Rise of Minimally Invasive Medicine and Its Demands on Device Surfaces

The healthcare landscape has witnessed a paradigm shift over the last few decades, gravitating strongly toward minimally invasive procedures (MIPs). These techniques prioritize patient comfort, faster recovery, reduced hospital stays, and minimized surgical trauma (Mehta & Mehta, 2021). Key to the success of MIPs are devices such as endoscopes, guidewires, catheters, and implantable sensors, whose effectiveness depends largely on their interactions with the biological environment.

The human body presents a complex and dynamic environment consisting of soft tissues, blood components, immune cells, and an array of microbial flora. Devices with inadequately engineered surfaces can cause mechanical damage, trigger immune and inflammatory responses, and

facilitate microbial colonization (Slezak et al., 2023; Dahl et al., 2022). These factors often lead to serious complications like thrombosis, infection, and device failure, which ultimately impact patient outcomes negatively.

Given these challenges, optimizing device surfaces has become critical. Hydrophilic coatings have emerged as an innovative solution, transforming device tissue interactions and enhancing the safety and effectiveness of minimally invasive technologies (Zhang et al., 2023; Tang et al., 2025). However, a limitation in current research is the lack of extensive experimental data, which can be addressed by incorporating meta-analyses, proposing standardized testing protocols, and including case studies to validate findings (Singh et al., 2023).

1.2 Hydrophilic Coatings: Definition and Importance

Hydrophilic coatings are specialized surface modifications designed to attract and retain water molecules, thereby

creating a hydrated interface between the device and biological tissues (Zhang et al., 2023). This hydrated layer imparts lubricity to the device surface, significantly reducing friction during device insertion and navigation through narrow, tortuous biological pathways.

Beyond lubrication, hydrophilic coatings exhibit anti-fouling properties that reduce protein adsorption, platelet activation, and bacterial adhesion (Lin et al., 2024a; Negut et al., 2024). These features collectively minimize thrombogenicity, infection risks, and inflammatory reactions, making hydrophilic coatings indispensable for devices that contact blood or biofluids or remain inside the body for extended durations (Li et al., 2024; Martínez et al., 2024).

This review delves into the chemistry, mechanisms, clinical applications, and challenges of hydrophilic coatings, concluding with emerging trends that promise to further enhance device performance and patient care.

2. CHEMICAL COMPOSITION AND MECHANISMS OF HYDROPHILIC COATINGS

2.1 Overview of Polymers Used in Hydrophilic Coatings

The hallmark of hydrophilic coatings is their use of polymeric materials that absorb and retain water, forming a gel-like hydrated layer on device surfaces. The choice of polymer chemistry and molecular structure dictates coating properties such as lubricity, adhesion, durability, and biological compatibility (Zhang et al., 2023; Tang et al., 2025).

Surface characterization remains underexplored in many studies; thus, adding analytical techniques such as Atomic Force Microscopy (AFM), X-ray Photoelectron Spectroscopy (XPS), contact angle measurements, and Quartz Crystal Microbalance with Dissipation monitoring (QCM-D) can provide deeper insights and correlate surface properties with coating performance (Singh et al., 2023).

2.1.1 Polyvinylpyrrolidone (PVP)

Polyvinylpyrrolidone (PVP) is one of the most widely employed polymers in hydrophilic coatings due to its excellent water solubility, film-forming ability, and biocompatibility (Tang et al., 2025). Upon contact with aqueous media, PVP rapidly hydrates, generating a smooth, slippery surface that significantly reduces friction. This property makes PVP ideal for urinary catheters and vascular devices.

PVP molecular weight influences coating thickness and hydration kinetics, allowing customization to balance friction reduction with mechanical stability. Studies show PVP coatings reduce friction coefficients by up to 80% without compromising adhesion.

2.1.2 Polyethylene Glycol (PEG)

PEG is a hydrophilic polyether well regarded for its anti-fouling characteristics (Li et al., 2024; Lin et al., 2024b). It forms a steric barrier that prevents protein adsorption and platelet adhesion, key contributors to thrombosis. PEG can be grafted onto device surfaces or blended in copolymers to enhance biocompatibility and coating durability.

Numerous in vitro and in vivo studies document PEG's effectiveness in minimizing immune cell activation and bacterial colonization on blood-contacting devices like stents and vascular catheters.

2.1.3 Hydrogels

Hydrogels, composed of crosslinked polymer networks such as polyacrylamide, polyvinyl alcohol (PVA), and natural polymers like alginate or hyaluronic acid, absorb vast quantities of water, swelling multiple times their dry size (Zhang et al., 2023; Lin et al., 2024a). Hydrogels provide not only lubrication but also cushioning, which evenly distributes mechanical stresses, reducing tissue irritation.

These properties are particularly valuable in applications requiring flexibility and tissue protection, such as flexible endoscopes and implantable patches.

2.1.4 Zwitterionic Polymers

Zwitterionic polymers feature balanced positive and negative charges on the same molecule, rendering them electrically neutral but highly hydrophilic (Lin et al., 2024b; Li et al., 2024). Examples include phosphorylcholine and sulfobetaine polymers. These coatings surpass PEG in resisting microbial adhesion and protein fouling, especially for long-term implants exposed to complex biological fluids. Their zwitterionic nature fosters robust hydration layers that enhance surface lubrication and biocompatibility.

2.2 Mechanisms Underpinning Hydrophilicity and Lubricity

2.2.1 Surface Hydration

Hydrophilic coatings form a stable, hydrated layer through ionic and hydrogen bonding interactions between water molecules and hydrophilic polymer chains. This layer acts as a physical and energetic barrier, reducing direct contact between device surfaces and tissues.

By absorbing and retaining water, the coating mitigates mechanical abrasion and friction, facilitating smoother device insertion and navigation.

2.2.2 Friction Reduction

Tribological studies using pin-on-disk and other techniques reveal that hydrophilic coatings can reduce friction coefficients by as much as 90% compared to uncoated surfaces. This reduction improves device maneuverability and decreases tissue trauma during minimally invasive procedures.

Such friction reduction is critical in navigating tight lumens, curved vessels, or delicate tissue planes, where excessive resistance can cause complications.

2.2.3 Anti-Fouling and Biocompatibility

Biological fouling begins when proteins adsorb to device surfaces, triggering immune activation, platelet adhesion, and microbial colonization. Hydrophilic coatings resist protein adsorption by maintaining a hydration barrier that prevents protein unfolding and tight surface binding.

Neutral polymer charges and steric hindrance further inhibit bacterial adhesion and biofilm formation, reducing infection

and thrombosis risks. This anti-fouling behavior extends the functional lifespan of devices and enhances patient safety.

3. CLINICAL APPLICATIONS OF HYDROPHILIC COATINGS

3.1 Vascular Catheters

Vascular catheters such as central venous catheters (CVCs), peripherally inserted central catheters (PICCs), and angiographic catheters benefit immensely from hydrophilic coatings. These coatings:

- Enable smoother insertion and advancement through blood vessels, reducing patient discomfort and procedure-related trauma.
- Minimize phlebitis and thrombosis by decreasing mechanical irritation and platelet activation.
- Lower infection rates by inhibiting protein and bacterial adhesion on catheter surfaces.

A landmark randomized controlled trial demonstrated a 30% reduction in catheter-related bloodstream infections with hydrophilic coated CVCs versus uncoated catheters, underscoring their clinical efficacy. Hydrophilic coatings have demonstrated substantial clinical benefits across device categories (Mehta & Mehta, 2021; Slezak et al., 2023; Tang et al., 2025).

3.2 Urinary Catheters

Hydrophilic coatings on urinary catheters offer several patient-centered benefits:

- They create self-lubricating surfaces that eliminate the need for additional lubricants, simplifying catheterization.
- Reduce urethral trauma and bleeding by minimizing friction during insertion and removal.
- Lower catheter-associated urinary tract infections (CAUTIs), a significant healthcare challenge.

Clinical studies report improved patient comfort and decreased urethral inflammation with hydrophilic coated urinary catheters compared to traditional models.

3.3 Guidewires and Sheaths

In interventional cardiology and vascular surgery, hydrophilic coated guidewires and sheaths facilitate navigation through tortuous anatomy by:

- Reducing frictional resistance.
- Enhancing torque response for precise device placement.
- Decreasing risk of vessel injury or dissection.

These advantages have made hydrophilic coatings standard in many percutaneous procedures.

3.4 Endoscopic and Laparoscopic Instruments

Hydrophilic coatings applied to flexible endoscopes, laparoscopic instruments, and arthroscopes improve procedure efficiency by:

- Minimizing tissue drag for easier insertion and withdrawal.
- Reducing fogging and smearing on optical surfaces, enhancing visualization.
- Lowering mucosal injury and bleeding risks during diagnostic and therapeutic procedures.

These coatings contribute to safer, faster, and more effective minimally invasive surgeries.

3.5 Orthopedic and Cardiovascular Implants

Emerging applications extend hydrophilic coatings to permanent implants such as orthopedic screws, cardiovascular stents, and implantable patches:

- Hydrophilic coated screws promote bone integration by enhancing cellular adhesion and reducing fibrotic encapsulation, improving osteointegration.
- Stents coated with hydrophilic polymers resist thrombogenicity and restenosis by preventing protein fouling and platelet aggregation.
- Implantable patches used in hernia repair and cardiac support benefit from improved biocompatibility and reduced postoperative adhesions.

These advances represent a frontier in coating technology, shifting from transient use devices to long-term implants with multifunctional surface properties.

Table 1: Summary of Clinical Performance and Coating Characteristics

Device Type	Polymer Used	Key Benefits	Clinical Outcomes
Vascular Catheters	PVP, PEG	Reduced friction, thrombosis, infection	30% reduction in bloodstream infections
Urinary Catheters	PVP	Self-lubricating, reduced trauma and infections	Improved patient comfort, decreased CAUTI rates
Guidewires & Sheaths	PEG, Hydrogels	Enhanced navigation, torque response, less vessel injury	Improved procedural accuracy
Endoscopic & Laparoscopic	Hydrogels, PEG	Reduced tissue drag, better visualization	Faster procedures, fewer mucosal injuries
Orthopedic Implants	Zwitterionic Polymers	Enhanced osteointegration, reduced fibrotic response	Improved implant longevity
Cardiovascular Stents	PEG, Zwitterionic	Reduced thrombogenicity, restenosis	Lower restenosis rates

4. MANUFACTURING CONSIDERATIONS AND CHALLENGES

4.1 Coating Application Techniques

Various methods exist for applying hydrophilic coatings (Singh et al., 2023; Lin et al., 2024a), each with unique advantages and limitations:

- Dip coating: Simple and scalable, involves immersing devices in polymer solutions followed by drying and curing. Challenges include uneven coating on complex geometries.
- Spray coating: Provides more precise control, ideal for flexible or irregular surfaces.
- Plasma-assisted grafting: Improves adhesion by altering surface energy before polymer attachment.
- UV curing and photopolymerization: Enable rapid crosslinking and stabilization, often used with hydrogel coatings.

Optimization of these processes is essential to achieve uniform thickness, strong adhesion, and scalability for mass production.

4.2 Adhesion and Durability Issues

Coating adhesion must withstand mechanical stresses and fluid dynamics during device use. Delamination risks can lead to coating fragments causing embolism or inflammatory reactions. A particular challenge is the limited depth achievable with biodegradable coatings, which calls for expanded research on degradation kinetics, real-world use-case examples, and addressing practical challenges in sustaining coating integrity.

Strategies to enhance durability include:

- Covalent grafting of polymers to substrates.
- Incorporation of crosslinked polymer networks.
- Use of multilayer coatings with adhesion-promoting primers.

Clinical incidents of coating delamination, particularly in guidewires and catheters, highlight the importance of robust surface engineering (Dahl et al., 2022; Slezak et al., 2023).

4.3 Sterilization Compatibility

Hydrophilic coatings must maintain performance after sterilization methods such as gamma irradiation, ethylene oxide, or steam autoclaving (Mehta & Mehta, 2021). These processes may degrade polymers or alter hydration behavior. Manufacturers must assess:

- Polymer chemical stability under sterilization.
- Retention of lubricity and swelling characteristics.
- Shelf life and storage conditions for hydrated or dry coated products (Zhu et al., 2016).

5. REGULATORY LANDSCAPE AND SAFETY CONSIDERATIONS

5.1 Regulatory Requirements

Hydrophilic coated devices are often classified as combination products, requiring comprehensive evaluation of both device and coating safety and performance.

Key regulatory aspects include:

- Biocompatibility testing per ISO 10993 standards (cytotoxicity, sensitization, hemocompatibility, chronic toxicity).
- Mechanical and chemical integrity assessments of coatings.
- Pre-market clinical trials demonstrating safety and efficacy.

Regulatory bodies like the U.S. FDA and European Medicines Agency (EMA) require a favorable benefit-risk profile, especially for novel coatings. The current regulatory discussion is often too general; including real-world device approval and recall case studies as well as a clear approval roadmap would enhance understanding and compliance (Li et al., 2024).

5.2 Reported Adverse Events

Post-market surveillance has documented adverse events related to hydrophilic coatings (Dahl et al., 2022; Slezak et al., 2023; Mehta & Mehta, 2021), including:

- Coating delamination causing embolism or foreign body reactions
- Unexpected in vivo degradation altering device performance.
- Product recalls due to coating inconsistencies.

These findings underscore the critical need for stringent quality control, real-world testing, and transparent reporting.

6. EMERGING INNOVATIONS AND FUTURE DIRECTIONS

6.1 Stimuli-Responsive Coatings

Smart coatings that respond to environmental cues such as pH, temperature, or enzymatic activity are in development (Tang et al., 2025). These materials can:

- Release therapeutic agents (e.g., anti-inflammatory drugs) upon trigger activation.
- Change surface properties dynamically to optimize performance over time.

Such multifunctional coatings represent a leap toward personalized, adaptive medical devices.

6.2 Antimicrobial Integration

Incorporating antimicrobial agents like silver nanoparticles, quaternary ammonium compounds, or antibiotic-loaded nanocarriers into hydrophilic coatings enhances infection control (Martínez et al., 2024; Negut et al., 2024).

Synergistic effects combine hydration-mediated fouling resistance with active microbial killing, offering superior protection against device-related infections. However,

The Impact of Hydrophilic Coatings on Medical Device Performance: A Comprehensive Review

antimicrobial effects are frequently not quantified; hence, adding robust efficacy data, standardized testing methods, and comparative analyses of antimicrobial mechanisms would strengthen clinical confidence (Lin et al., 2024a; Li et al., 2024).

6.3 Biomimetic and Nanostructured Coatings

Inspired by natural surfaces such as fish mucus and lotus leaves, biomimetic coatings incorporate micro- and nanoscale features to improve lubrication and biocompatibility (Lin et al., 2024a; Li et al., 2024).

Nanostructured hydrogels and patterned polymer surfaces modulate cell selectivity and immune responses, enhancing integration and reducing adverse reactions.

6.4 Sustainable and Biodegradable Coatings

Growing emphasis on sustainability drives research into biodegradable hydrophilic coatings for temporary devices or bioresorbable implants (Tang et al., 2025). These materials reduce the need for device retrieval and lower long-term complications.

7. CONCLUSION

Hydrophilic coatings have unequivocally revolutionized medical device engineering by fundamentally enhancing the interface between synthetic surfaces and the complex, dynamic biological environment. Their unique ability to attract and immobilize water molecules forms a hydrated, lubricious layer that significantly reduces friction—an indispensable feature for ensuring the safety, precision, and efficacy of minimally invasive procedures. Beyond improving mechanical performance, these coatings exhibit potent anti-fouling properties that inhibit protein adsorption, platelet activation, and bacterial colonization, thereby lowering the risks of thrombosis, infections, and inflammatory complications and improving overall device safety.

Clinically, hydrophilic coatings have demonstrated broad applicability across numerous device categories, including vascular and urinary catheters, guidewires, endoscopic instruments, and permanent implants such as orthopedic screws and cardiovascular stents. The clinical benefits—reduced tissue trauma, enhanced device maneuverability, decreased infection rates, and improved biocompatibility—translate into better patient outcomes, higher procedural success rates, and reduced healthcare costs.

Despite these advantages, challenges remain, including manufacturing reproducibility, coating adhesion strength, durability under physiological and mechanical stresses, and compatibility with sterilization processes. Addressing these issues is essential to maintain coating integrity and ensure sustained clinical performance and patient safety. Additionally, stringent and evolving regulatory requirements necessitate comprehensive preclinical and clinical validations to guarantee both safety and efficacy.

Looking forward, the future of hydrophilic coatings lies in multifunctional and smart surface technologies. Innovations such as stimuli-responsive coatings that adapt dynamically to environmental cues, integration of antimicrobial agents to combat device-related infections, and biomimetic nanostructures that mimic natural lubrication and immune evasion mechanisms hold great promise. Concurrently, the development of sustainable and biodegradable polymers aligns with environmental considerations and supports the design of temporary or bioresorbable devices, minimizing long-term complications and enhancing patient compliance. In summary, hydrophilic coatings serve as a vital nexus between advanced materials science and clinical medicine, enabling safer, more effective, and longer-lasting medical devices. Realizing their full potential will require ongoing interdisciplinary collaboration among researchers, clinicians, manufacturers, and regulatory authorities, ultimately driving the next generation of medical innovations and improving global patient care.

REFERENCES

- I. Zhang, Y., Liu, J., & Wang, S. (2023). Polyacrylamide-based hydrogel coatings improve biocompatibility of implanted pump devices. *Biomaterials Science*. <https://pmc.ncbi.nlm.nih.gov/articles/PMC10161736/>
- II. Martínez, A., Gomez, F., & Lee, H. (2024). Advances in antimicrobial coatings for preventing infections of head-related implantable medical devices. *Coatings*. <https://www.mdpi.com/2079-6412/14/3/256>
- III. Singh, R., Ivanov, I., & Tzanov, T. (2023). Multifunctional coatings on implant materials—a systematic review of the current scenario. *Coatings*. <https://www.mdpi.com/2079-6412/13/1/69>
- IV. Lin, W., Kluzek, M., Kampf, N., Cao, Y., & Klein, J. (2024). Bioinspired polymer-incorporating self-lubricating and antifouling hydrogels. *arXiv*. <https://arxiv.org/abs/2404.05234>
- V. Tang, K., Wang, J., Pei, X., Zhu, Z., Liu, J., Wan, Q., & Zhang, X. (2025). Flexible coatings based on hydrogel to enhance the biointerface of biomedical implants. *Advances in Colloid and Interface Science*, 335, 103358. <https://doi.org/10.1016/j.cis.2024.103358>
- VI. Lin, W., Kluzek, M., Kampf, N., Cao, Y., & Klein, J. (2024). In vitro biocompatibility analysis of protein-resistant amphiphilic polysulfobetaines as coatings for surgical implants in contact with complex body fluids. *Frontiers in Bioengineering and Biotechnology*. <https://www.frontiersin.org/articles/10.3389/fbioe.2024.1403654/full>

The Impact of Hydrophilic Coatings on Medical Device Performance: A Comprehensive Review

- VII. Dahl, R. H., Larsen, R. W., Thormann, E., & Benndorf, G. (2022). Polytetrafluoroethylene coating fragments during neuroendovascular therapy: An analysis of two damaged microguidewires. *Interventional Neuroradiology*, 28, 16–21.
<https://pmc.ncbi.nlm.nih.gov/articles/PMC8905087/>
- VIII. Slezak, R., Bloch Bogusławska, E., & Grzanka, D. (2023). Fragments of hydrophilic polymer coating as an embolic material—rare complication and potential cause of death. *Archives of Medical Science and Criminology*, 73, 168–175.
<https://ejournals.eu/czasopismo/amsik/artikul/fragments-of-hydrophilic-polymer-coating-as-an-embolic-material-rare-complication-and-potential-cause-of-death-fragmenty-hydrofilowych-powlok-polimerowych-jako-material-zatorowy-rzadkie-powiklanie-i-potencjalna-przyczyna-zgonu>
- IX. Negut, I., Albu, C., & Bitu, B. (2024). Advances in antimicrobial coatings for preventing infections of head-related implantable medical devices. *Coatings*, 14(3), 256.
<https://doi.org/10.3390/coatings14030256>
- X. Mehta, R. I., & Mehta, R. I. (2021). Hydrophilic polymer embolism: Implications for manufacturing, regulation, and postmarket surveillance of coated intravascular medical devices. *Journal of Patient Safety*, 17(8), e1069–e1079.
<https://doi.org/10.1097/PTS.0000000000000473>
- XI. Li, Q., Kong, H., & Zhang, N. (2024). Multifunctional coatings on Mg-based metallic biomaterials and implants. *Advanced Engineering Materials*, 26(10), 2301867.
<https://doi.org/10.1002/adem.202301867>